

Distinct charge and spin gaps in underdoped $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ from analysis of NMR, neutron scattering, tunneling and quasiparticle relaxation experiments.

D.Mihailovic, V.V.Kabanov, K.Žagar and J.Demsar
*Solid State Physics Dept., "Jozef Stefan" Institut, Jamova 39, 1001
Ljubljana, Slovenia
(February 1, 2008)*

A systematic quantitative comparison of "pseudogap" values obtained from the analysis of charge and spin excitation spectroscopies in underdoped $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ using a temperature-independent gap shows *two distinct excitations*, one visible in spin-flip spectroscopies like NMR and spin polarized neutron scattering, and the other in charge excitation spectroscopies like single particle tunneling and time-resolved quasiparticle relaxation. Both appear to decrease with doping x approximately as $1/x$ and are T -independent, existing above and below T_c . We suggest that the charge excitation can be attributed to a pair-breaking local gap, while the spin excitation can be explained by an intra-gap local triplet state.

The term "pseudogap" Δ_p in the context of the cuprate superconductors usually refers to the observation of a change from "normal metallic" behaviour of some measured quantity, which occurs at some temperature T^* above the superconducting T_c . It has been observed by many different experimental techniques ranging from NMR¹⁻³, specific heat⁴, single-particle (SP) tunneling⁵ to angle-resolved photoemission (ARPES)⁶ and optical conductivity⁷. Such an effect can arise if for some reason a depression in the density of states (DOS) appears, giving rise to a change in the excitation spectrum, usually a depression in the generalized susceptibility, single particle spectral density, optical conductivity etc. However, an alternative view - recently proposed on the basis of femtosecond quasiparticle relaxation measurements (QPR) in YBa₂Cu₃O_{7- δ} ^{8,9} - is that in fact a *temperature-independent* single-particle (or pair-breaking) gap Δ_p exists at all temperatures in the underdoped state and the appearance of the pseudogap arises because of a statistical population effect for SP excitations across Δ_p . When the data were interpreted this way, remarkable agreement was found between the values of Δ_p , with other measurements where SP charge excitations are probed. For example, QPR measurements and SP tunneling give virtually the same Δ_p in YBCO, while SP tunneling and ARPES also agree quantitatively in Bi₂Sr₂CaCu₂O₈. However, the pseudogap Δ_s as observed by NMR and spin-polarized neutron scattering, where spin excitations are probed, appears to be smaller than the optical and tunneling pseudogap Δ_p for which so far there is no accepted explanation. Thus in spite of the availability of spectral data over a large range of doping there is an emerging apparent discrepancy in the size of the pseudogap.

In this communication, we present a quantitative analysis of the NMR Knight shift K_s in the underdoped state along the lines originally suggested by Alexandrov and Mott^{10,12} for the analysis of the "spin-gap" from the temperature-dependence of the NMR relaxation time T_1 . We use the same type of T -independent gap which extends above T_c (and T^*) as was used to analyze the time-resolved quasiparticle relaxation data⁸. The aim is to see if a) the simple model can describe the T -dependence of K_s and b) the values of the pseudogap Δ obtained for the NMR K_s agree quantitatively with values obtained from charge excitation spectroscopy and in particular quasiparticle relaxation measurements, where data for a wide range of doping now exist^{8,9}. When we compare the results with other experiments, we find that the charge excitation spectroscopies (QP relaxation, Gievers tunneling and ARPES) all consistently show a pseudogap Δ_p at approximately twice the size of the spin gap Δ_s (from NMR, neutron scattering) over a wide range of doping. To explain this observation we propose that the two gaps correspond to two distinct excitations.

The uniform susceptibility for the case of a pair ground state is given by the standard equation:

$$\chi_s(T) = -2\mu_B^2 \int_0^\infty dE N_s(E) \frac{\partial f_s}{\partial E}. \quad (1)$$

Here $f_s = [y^{-1/2} \exp(E/k_B T + \Delta_p/k_B T) + 1]^{-1}$ is the distribution function for electrons (or holes), $y = \exp[\mu(T)/k_B T]$, $\mu(T)$ is the pair chemical potential, $N_s(E)$ is the single particle DOS, $2\Delta_p$ is the pair binding energy and μ_B the Bohr magneton. Since the pairing energy (or "pseudogap") Δ_p is expected to be of the order of a few hundred kelvin, we can assume that single electrons are non-degenerate, and

$$f_s \simeq y^{1/2} \exp\left(-\frac{E + \Delta_p}{k_B T}\right). \quad (2)$$

We assume that the single particle DOS can be approximated by:

$$N_s(E) = C E^\alpha \quad (3)$$

where C is constant, which is in general weakly doping dependent, and α is an exponent which characterizes the shape of the single particle spectrum near the single particle band edge and is typically between -1 and -1/2. Substituting Eqs.(2) and (3) into Eq.(1) we derive the expression for the uniform susceptibility:

$$\chi_s(T, x) = C \mu_B^2 y^{1/2} (k_B T)^\alpha \exp\left(-\frac{\Delta_p}{k_B T}\right). \quad (4)$$

In general, y is a smooth function of temperature, and in the case of high- T_c superconductors it has been argued¹¹ that y is constant. Assuming that paired states are non-degenerate above T_c , we can write that $y = n_p(T)/k_B T N_p(0)$, where $n_p(T)$ is the density of pairs at temperature T and $N_p(0)$ is the density of states, which is assumed to be constant. Then approximating $n_p(T) \sim T$ (which also gives the correct $1/T$ dependence for the Hall coefficient), we expect that y is constant over a wide temperature range. (The same temperature independent behaviour of y is expected if the chemical potential is pinned by a large DOS in a narrow band.) As a result, Eq. (4) provides a general expression for the susceptibility of a system with a paired ground state and unpaired excited state.

From the point of view of the analysis of susceptibility data it is important to note that formula (4) for a pairing gap is essentially the same as the susceptibility due to a bound local triplet state above a singlet paired ground state, namely $\chi_s^{S-T}(T) \sim 1/T \exp[-J/k_B T]$ ¹². Unfortunately this means that a *pairing gap cannot be distinguished from a spin-flip gap* on the basis of susceptibility measurements alone.

We can now write a rather general formula for the Knight shift which is valid irrespective of the origin of the gap and which can apply for *either* a pairing gap or a spin singlet-triplet gap:

$$K_s = K_0 + A T^\alpha \exp[-\Delta/k_B T], \quad (5)$$

where K_0 is the value of K_s at zero temperature, and Δ is either Δ_p or $\Delta_s = J$. (In fact this formula is valid).

We now proceed by examining the NMR Knight shift data for different nuclei in YBCO. Fits to the data on $\text{YBa}_2\text{Cu}_4\text{O}_8$ over a very wide range of temperatures for ^{63}Cu by Curro et al² and up to room temperature for ^{17}O by Williams et al³ are shown in Figure 2 using both $\alpha = -1/2$ and $\alpha = -1$. Both fits give good agreement with the data over a very wide range of temperatures; up to 700 K in the case of ^{63}Cu . Although the fit with $\alpha = -1/2$ appears to be slightly better at high temperatures than with $\alpha = -1$, this should be treated with caution, since at high temperatures there may be oxygen loss in the sample, which could probably affect the measurements to some extent. The choice of α affects the value of Δ which is obtained from the fit however, and with $\alpha = -1$, Δ can be significantly smaller than with $\alpha = -1/2$, as indicated in Fig. 1a). Nevertheless, we conclude that in spite of its simplicity, the model appears to describe the data very well over a wide range of temperatures, provided the absolute value of the gap obtained from the fit is treated with caution.

Extending the analysis as a function of doping, the K_s data for ^{89}Y NMR¹ on $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ over a wide range of δ are shown in Fig. 1 b). All the data can be fit with Eq. (5) using only Δ as an adjustable parameter. In Fig. 2a) we plot the gap values Δ as a function of δ with both $\alpha = -1/2$ and $\alpha = -1$. As before, Δ appears consistently lower with $\alpha = -1$ than with $\alpha = -1/2$ by approximately 100K. Reassuringly, the values of Δ obtained from all the different fits for the different nuclei in Figs. 1a) and 1b) on YBCO-123 and 124 are quite consistent with each other, which gives us confidence regarding the validity of the approach to susceptibility analysis using a T -independent gap.

In order to interpret the origin of the gap obtained from the analysis of the NMR Knight shift, we now compare these data with other spectroscopies. In Figure 3 we have plotted the gap as a function of δ from NMR K_s , spin-polarized neutron scattering (SPNS), tunneling and quasiparticle relaxation measurements. SPNS shows a spin-excitation peak at $E_s=34$ meV (~ 390 K) in underdoped $\text{YBa}_2\text{Cu}_3\text{O}_{6.6}$ ¹³, which agrees very well with the spin-flip gap from K_s . On the other hand, the gap values Δ_p from *both* single-particle tunneling and QPR experiments appear to be significantly larger than Δ , by as much as a factor of 2, which strongly suggests that the spin-flip "gap" in NMR and SPNS, and the quasiparticle gap from QPR and tunneling arise from *different excitations*.

This hypothesis is strongly supported by recent neutron scattering data of Mook et al. for $\delta = 0.4$ ¹³. In the neutron scattering phonon spectra of $\text{YBa}_2\text{Cu}_3\text{O}_{6.6}$ there appear to be anomalies which signify the presence of *charge* excitations interfering with phonons. For $\delta = 0.4$, the anomaly occurs near 70 meV (~ 810 K), which agrees remarkably well with the Δ_p from QPR and SP tun-

neling experiments. Neutron scattering thus appears to show the presence of both "gaps", one due to charge excitations and the other due to spin excitations.

In order to explain the presence of two different "gaps" Δ_p and Δ_s , we start from the original suggestion by Alexandrov and Mott some years ago for the existence of a triplet state¹⁰ to propose an electronic structure of YBaCuO . A schematic diagram is shown in the insert to Fig. 3. The ground state is composed of *local* $S=0$ singlet pairs. Since Δ_p is a single-particle charge excitation, it is clearly associated with pair breaking^{8,5}. However, if $J < \Delta_p$, the triplet local pair state also exists and lies within the gap. It should be visible by spin-flip spectroscopies like NMR and SPNS, but not by optical spectroscopy or SP tunneling. We propose therefore that the Δ_s observed by NMR and SPNS is due to a $S=1$ *local pair* triplet excited state which lies approximately in the middle of the gap. From the experimental data in Fig. 4, both Δ_p and Δ_s decrease with increasing doping, more or less as $1/x$, where x is the hole density. This is consistent with a reduction of both the pair-binding energy Δ_p and the exchange coupling J on the basis of simple screening arguments¹¹. For low oxygen doping, at $\delta \sim 0.6$, $J/k_B \approx 800\text{K}$, consistent also with 2-magnon Raman scattering measurements¹⁴. A rather remarkable feature of these analysis is that a large body of data on both spin and charge excitation spectroscopies can be described quantitatively by a very simple model using an isotropic temperature-independent gap.

We conclude by noting that although we have found that $\Delta_s = J \simeq \Delta_p/2$ in $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$, the situation might well be different in other materials. In $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ for example, the optical gap and the NMR gap appear to have the same energy scale¹⁵, suggesting that either $J \gtrsim \Delta_p$, or that the triplet pair state is not a bound state. It will be interesting to see if analysis of other materials might lead to some systematic connection between Δ_p , J and T_c .

FIG. 1. The Knight shift K_s as a function of temperature a) in $\text{YBa}_2\text{Cu}_4\text{O}_8$ ($T_c=81$ K). The solid squares are for ^{63}Cu from Curro et al² and the open circles for ^{17}O from Williams et al³. The parameters used in the fits with Eq. 5 are given in the figure. b) The ^{89}Y NMR K_s as a function of temperature in $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ for different δ ¹. The fits with $\alpha = -1$ and $\alpha = -1/2$ are indistinguishable on the plot, but give different values of Δ .

FIG. 2. The energy gap(s) Δ as a function of doping δ . The circles are for $\alpha = -1$ and the squares for $\alpha = -1/2$.

FIG. 3. The charge and spin gaps Δ_p and Δ_s respectively, as a function of doping. The full circles are from ^{89}Y NMR K_s . The open squares are from time-resolved QP relaxation measurements^{8,9}. The open and full diamonds are the SPNS and charge excitation neutron data respectively, while the triangles are from tunneling data⁵.

-
- ¹ H.Alloul, T.Ohno, P.Mendels, Physica C **162-164**, 193 (1990)
- ² N.J.Curro et al, Phys.Rev. B **56**, 877 (1997)
- ³ G.V.M.Williams et al, Phys.Rev.Lett. **78**, 721 (1997)
- ⁴ J.W.Loram et al, J.Supercond. **7**, 243 (1994)
- ⁵ G.Deutscher, Nature **397**, 410 (1999)
- ⁶ M.R.Norman, Phys.Rev.B **57**, R11093 (1998)
- ⁷ D.Mihailovic, T.Mertelj and K.A.Müller, Phys.Rev.B **57**, 6116 (1998)
- ⁸ V.V.Kabanov, et al Phys.Rev.B **59**, 1497 (1999), J.Demsar et al, Europhys. Lett. **45**, 381 (1999)
- ⁹ J.Demsar, B. Podobnik, V.V. Kabanov, D. Mihailovic and T.Wolf, Phys. Rev. Lett. **82**, 4918 (1999)
- ¹⁰ A.S.Alexandrov and N.F.Mott, Rep.Prog.Phys. **57**, 1197 (1994)
- ¹¹ A.S.Alexandrov, V.V.Kabanov and N.F.Mott, Phys. Rev.Lett. **77**, 4796 (1996)
- ¹² A.S. Alexandrov, Physica C **182**, 327, (1991)
- ¹³ H.Mook et al., Nature **395**, 580 (1998), the data for the phonon anomalies were presented at HTS99, Miami (1999)
- ¹⁴ see for example G.Blumberg et al., **49**, 13295 (1994), *ibid.* 15385
- ¹⁵ K.A.Müller, Guo-meng Zhao, K.Conder and H.Keller, J.Phys.:Condens.Matter **10**, L291 (1998)

Fig 1





Fig.2




Fig.3

